

## 5000

Solvent Base Epoxy



**CruSPEC 5000** is an extremely durable, surface tolerant, easy to apply epoxy. Excellent abrasion, chemical resistance, & Low VOC. Brush, roll, or spray.

Available in white, light gray, safety yellow, and hundreds of custom colors.

### FEATURES AND BENEFITS

- Chemical resistant
- Abrasion resistant
- Immersion service
- Surface tolerant
- Low VOC
- Brush, roll, or spray application

### USES

- Chemical Containment
- Loading Docks
- Equipment
- Floors
- Mezzanines
- Tanks



216-531-0710



info@continentalpaints.com



## PHYSICAL PROPERTIES

Part A Product Code	96-4450
Part B Product Code	96-0228
Volume Solids	Part A: 45.3 ±2.0% Part B: 39.0 ±2.0% Blended: 43.2 ±2.0%
Gloss @ 60 °	>70 @ 1 - 1.5 mils DFT
Mixing Ratio	2 parts: 96-4450 1 part: 96-0228
Viscosity @ 77 °F (blended by volume)	20-27 seconds #3 Zahn Signature Cup
VOC	Part A: 1.45lbs/gal 170.0 g/l Part B: 0.0 lbs/gal 0.0 g/l Blended: 0.97 lbs/gal 113.7 g/l
Spreading Rate	692 sq ft/gal @ 1 mil DFT
Recommended DTM film thickness	Mils Wet: 4.0 - 5.0 mils Miles Dry: 1.6 - 2.0 mils Mils Max: 6 mils
Drying	Set to Touch: 10 - 15 minutes Tack Free: 20 - 25 minutes To Handle: 1 - 2 hours Total (full properties) 24 hours
Working potlife	1.5 hours @ 75 °F; 10 hours 85 °F

## STAY CONNECTED



@CoatingsPros



@ContinentalProductsCo



@coatingspros




Continental Products



ContinentalPaints.com

2926 Chester Avenue  
Cleveland, Ohio 44114  
Headquarters: 440-605-1020  
f: 440-605-1120  
Manufacturing Plant: 216-531-0710  
f: 216-289-1745

Part of the  Performance Coatings Family  
crupc.com

© 2021 Continental Products™, all rights reserved. Printed in U.S.A. All logos/images are trademarks of Continental Products. Cleveland, OH USA.



216-531-0710



info@continentalpaints.com