

9000

Two Component Urethane



Cru<Spec 9000 has excellent gloss and color retention. Outstanding corrosion, chemical, and abrasion resistance. Brush, roll, or spray.

Available in white, black, safety yellow, safety red, and hundreds of custom colors, low Voc.

FEATURES AND BENEFITS

- Excellent gloss retention
- Excellent color retention
- Corrosion resistant
- Chemical resistant
- Low VOC
- Quick dry
- Brush, roll, or spray application

USES

- Towers
- Trailers
- Tanks
- Doors & Trim
- Trucks
- Equipment
- Machinery
- Signs



216-531-0710



info@continentalpaints.com



PHYSICAL PROPERTIES

Part A Product Code	96-4450
Part B Product Code	96-0228
Volume Solids	Part A: 45.3 ±2.0% Part B: 39.0 ±2.0% Blended: 43.2 ±2.0%
Gloss @ 60 °	>70 @ 1 - 1.5 mils DFT
Mixing Ratio	2 parts: 96-4450 1 part: 96-0228
Viscosity @ 77 °F (blended by volume)	20-27 seconds #3 Zahn Signature Cup
VOC	Part A: 1.45lbs/gal 170.0 g/l Part B: 0.0 lbs/gal 0.0 g/l Blended: 0.97 lbs/gal 113.7 g/l
Spreading Rate	692 sq ft/gal @ 1 mil DFT
Recommended DTM film thickness	Mils Wet: 4.0 - 5.0 mils Miles Dry: 1.6 - 2.0 mils Mils Max: 6 mils
Drying	Set to Touch: 10 - 15 minutes Tack Free: 20 - 25 minutes To Handle: 1 - 2 hours Total (full properties) 24 hours
Working potlife	1.5 hours @ 75 °F; 10 hours 85 °F

STAY CONNECTED



@CoatingsPros



@ContinentalProductsCo



@coatingspros



Continental Products



ContinentalPaints.com


2926 Chester Avenue
Cleveland, Ohio 44114

Headquarters: 440-605-1020

f: 440-605-1120

Manufacturing Plant: 216-531-0710

f: 216-289-1745

Part of the  Performance Coatings Family
crupc.com

© 2021 Continental Products™, all rights reserved. Printed in U.S.A. All logos/images are trademarks of Continental Products. Cleveland, OH USA.



216-531-0710



info@continentalpaints.com