



8000

Waterborne
Industrial Maintenance Enamels



Cru<Spec 8000 is a highly durable, easy to apply maintenance enamel. Outstanding corrosion resistance in DTM applications. Excellent adhesion, fade resistance, abrasion resistance, & low VOC. Brush, roll, or spray.

Available in white, black, safety yellow, safety red, and hundreds of custom colors.

FEATURES AND BENEFITS

- Quick dry
- Corrosion resistant
- Excellent adhesion
- Fade resistant
- Low VOC
- Brush, roll, or spray application

USES

- Doors & Trim
- Machinery
- Pipes
- Walls
- Equipment
- Handrails



216-531-0710






info@continentalpaints.com




PHYSICAL PROPERTIES

| | |
|---------------------------------------|---|
| Part A Product Code | 96-4450 |
| Part B Product Code | 96-0228 |
| Volume Solids | Part A: 45.3 ±2.0% Part B: 39.0 ±2.0% Blended: 43.2 ±2.0% |
| Gloss @ 60 ° | >70 @ 1 - 1.5 mils DFT |
| Mixing Ratio | 2 parts: 96-4450 1 part: 96-0228 |
| Viscosity @ 77 °F (blended by volume) | 20-27 seconds #3 Zahn Signature Cup |
| VOC | Part A: 1.45lbs/gal 170.0 g/l Part B: 0.0 lbs/gal 0.0 g/l Blended: 0.97 lbs/gal 113.7 g/l |
| Spreading Rate | 692 sq ft/gal @ 1 mil DFT |
| Recommended DTM film thickness | Mils Wet: 4.0 - 5.0 mils Miles Dry: 1.6 - 2.0 mils Mils Max: 6 mils |
| Drying | Set to Touch: 10 - 15 minutes Tack Free: 20 - 25 minutes To Handle: 1 - 2 hours Total (full properties) 24 hours |
| Working potlife | 1.5 hours @ 75 °F; 10 hours 85 °F |

STAY CONNECTED

-  @CoatingsPros
-  @ContinentalProductsCo
-  @coatingspros
-  Continental Products
-  ContinentalPaints.com

2926 Chester Avenue
Cleveland, Ohio 44114
Headquarters: 440-605-1020
f: 440-605-1120
Manufacturing Plant: 216-531-0710
f: 216-289-1745

Part of the  Performance Coatings Family
crupc.com

© 2021 Continental Products™, all rights reserved. Printed in U.S.A. All logos/images are trademarks of Continental Products. Cleveland, OH USA.



216-531-0710



info@continentalpaints.com